

655 GREASE

Silicone grease for rubber to metal lubrication and sealing of dynamic O-rings primarily in pneumatic systems

Applications

Primarily designed to provide a controlled rubber swell and ensure that rubber connections such as O-rings and seals in pneumatic systems form tight seals.

Its wide operating temperature, resistance to oxidation, corrosion and hydrolytic stability make it ideally suited for dynamic between rubber and metal parts in pneumatic systems of all aviation, industrial and automotive equipment.

Benefits

- Extremely wide service temperature range of -65°C to +175°C
- Exceptionally good oxidation resistance
- High shear stability
- Swells rubber to a controlled degree for better sealing effect
- Resistant to ageing, water, moisture, steam, humidity and corrosive environments
- Low evaporation and bleed characteristics
- Excellent resistance to oxidation
- Safe for use on metal, plastic and rubber components

Directions for Use

Use as supplied. Never dilute or mix with other oil or grease. Apply on all clean sliding surfaces by normal greasing methods i.e. by brush, grease gun or dispense via centralized lubrication systems. Check compatibility with plastics prior to use.

655 GREASE

TECHNICAL PROPERTY

| Parameter | Value | Unit | Standard |
|---|---------------------------|-------------------|-----------------|
| Type | Synthetic silicone grease | | |
| Appearance | Smooth grease | | |
| Base oil | Silicone / Ester | | |
| Thickener | Lithium soap | | |
| Color ¹ | Tan | | |
| Penetration, worked | 265-295 | mm/10 | ASTM D 217 |
| NLGI consistency | 2 | Class | DIN 51 818 |
| Density, @ 25°C | 0.95-0.98 | g/cm ³ | |
| Drop point | +215 | °C | ASTM D 566 |
| Service temperatures | -65 to +175 | °C | |
| Copper strip corrosion | 1a, pass | | ASTM D 130 |
| Water resistance, static evaluation | 0-90 | | DIN 51 807 pt.1 |
| Bleed, 24h. 150°C | 3 | % | |
| Evaporation, 24h. 150°C | 1.5 | % | |
| Oxidation resistance, 100 h, 99 °C, pressure drop | 0.1 | bar | DIN 51 808 |

1. Minor color variation of the same product but of different batches could be possible. However the lubrication values remain unchanged.

General

Use in well ventilated areas. Avoid continuous breathing of vapor and spray mist. In closed areas or areas with poor ventilation, use respiratory protection. For complete details on safety, short and long term exposure, refer to this product's safety data sheet (SDS).

Disposal

All used and unused product should be disposed of in accordance with state regulations.

Handling

Read instructions on the container label of the product before use. The product safety data sheet (SDS) contains the relevant information regarding personal protective equipment, safe use, physical and health hazards. Safety data sheet is available from ASV or your local ASV distributor.

Manufactured by
ASV Multichemie Private Limited
W 46, TTC Industrial Area, MIDC Rabale,
Navi Mumbai 400 701 INDIA
Contact: +91 22 2764 2516
Email: info@asvmultichemie.com

Available Packaging

100 g, 1 kg

Shelf Life

36 months from date of manufacture in sealed condition.

Limited Warranty

The information and data contained in this sheet is accurate to the best of our knowledge or is obtained from sources, tests or experiences believed by us to be reliable and accurate. User is responsible for determining whether recommended ASV product is fit for a particular purpose. All products should be tested for suitability on a particular application prior to actual use. We make no representations of any kind. Data offered without warranty. Product manufactured is for industrial use only.

WWW.ASVMULTICHEMIE.COM

ASV® MOLYSULF® PENETROIL® SHINY GALVA® VALV-KOTE® BRIGHT ZINK® SPEZET® MOLYCHEM® TRIBOSULF® are Registered Trademarks of ASV MULTICHEMIE PRIVATE LIMITED, INDIA.
ALL DATA OFFERED WITHOUT LIABILITY OR WARRANTY.