

MOLYKOTE® G-N PLUS Solid Lubricant Paste

Solid lubricant paste for the assembly and running-in of metal components

Features & benefits

- High load-carrying capacity
- Low coefficient of friction
- Prevents frictional corrosion and scoring
- Protection from stick-slip
- Good anti-corrosion properties
- Reduces formation of fretting corrosion
- Simplifies dismantling processes
- High surface-covering capacity (40 m²/kg)
- No intentional polytetrafluoroethylene (PTFE) or per- and polyfluoroalkyl substances (PFAS)

Composition

- Mineral oil
- Solid lubricants
- Thickener

Applications

Press-fit production of all types of machine elements, as a running-in lubricant for new machines and gearboxes. Permanent lubrication of machine elements that are moved only rarely or slightly and also for drilling, sawing and thread cutting. Used successfully for lubricating threaded spindles, splined shafts, toothed gears, worm and transmission gears, screws, valves, pumps, and machine-tool guides and also for the tightening and fitting of roller bearings, washers, wheels, flanges and bolts.

How to use

Clean the sliding surfaces or contact areas, then apply paste with a brush, cloth, synthetic sponge or window leather. Do not use in excess as with grease lubrication. Vigorous rubbing into metal surface will improve adhesion. Do not mix with greases or oils.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Unit	Result
	Color		Black
Penetration, density			
ISO 2137	Unworked penetration	mm/10	280–310
ISO 2811	Density at 20°C (68°F)	g/ml	1.35
Temperature			
	Service temperature ⁽²⁾	°C	-25 to +450 with reduced air access +630
		°F	-13 to +842 with reduced air access +1,166
Load-carrying capacity, wear protection, service life			
Four-ball tester			
DIN 51 350 pt.4	Weld load	N	2,800
DIN 51 350 pt.5	Wear scar under 800 N load	mm	0.75
Almen-Wieland machine			
	OK load	N	> 20,000
	Frictional force	N	2,600
Coefficient of friction			
	Press-fit test	μ	0.08, no chatter
Screw test: Erichsen ⁽³⁾			
	Screw test - μ thread		0.12
	Screw test - μ head		0.06
Resistance			
DIN 51 807 pt.1	Water resistance, static, evaluation		2-90

⁽¹⁾DIN: Deutsche Industrie Norm. ISO: International Standardization Organization ASTM: American Society for Testing and Materials.

⁽²⁾Temperature resistance of solid lubricants.

⁽³⁾Coefficient of friction in bolted connection, M12, 8.8, on blackened surface.

Usable life and storage

When stored between 0°C and 40°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

Packaging

This product is available in different standard container sizes as shown on [molykote.com](https://www.molykote.com). Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 1997-2024 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.